

METRIC FELT COMPANY

T E C H N I C A L D A T A


B96-STD (Part # 2049sl)

POLYPROPYLENE SUPPORTED LAMINATING ADHESIVE

DESCRIPTION

B96-STD is a supported, general purpose, rubber-base laminating adhesive designed for use on based

TAPE CONSTRUCTION



TYPICAL ADHESIVE PERFORMANCE DATA

PEEL ADHESION (PSTC-101)	LINER SIDE		UNWIND SIDE	
15 MINUTE APPLIED (oz./in.)	1	30-150	1	35-155
24 HOUR APPLIED (oz./in.)	1	40-160	1	45-165

SHEAR ADHESION (PSTC-107)		
1" X 1", 1,000 GRAMS, 72 DEGREES F (Hours)	24+	24+

MINIMUM APPLICATION TEMPERATURE 50 DEGREES F

NO LOAD APPLIED, SERVICE TEMPERATURE RANGE
-30 TO 125 DEGREES F CONTINUOUS
-40 TO 185 DEGREES F SHORT TERM

NOTE: Performance data indicates average production values from stainless steel and should not be used for minimum specification values. It is required that the converter determines suitability of tape prior to use.

DATE: 8/26/04 igc

The information contained herein is to the best of our knowledge and belief, accurate. However, since the conditions of handling and of use are beyond our control, we make no guarantee of results and assume no liability for damages incurred by following these suggestions. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations.

B96-STD INDUSTRIAL